

CE



[www.BeA-Group.com](http://www.BeA-Group.com)

2012

EN 14592/A1

Circular smooth shank nails for timber

Diameter = 2,8 mm    Length = 34 - 90 mm

**Properties of the material used:**

- non alloy wire rod in accordance with EN 10016-1 to 4
- tensile strength in accordance with EN 10218-1, min. 600 N/mm<sup>2</sup>

**Mechanical strength and stiffness:**

- Yield moment:  $M_{y,k} = 2.617,5 \text{ Nmm}$
- Withdrawl parameter:  $f_{ax,k} = 2,45 \text{ N/mm}^2$   
in timber of characteristic density 350 kg/m<sup>3</sup>
- Head pull-through parameter:  $f_{head,k} = 8,58 \text{ N/mm}^2$   
in timber of characteristic density 350 kg/m<sup>3</sup>

**Durability (corrosion-resistance):**

Electrogalvanized (Service Class 2 according to EN 1995-1-1)